# **NICKEL ALLOY**

# 825 - 2,4858



#### 825 - 2,4858

Nickel Alloy 825 is a nickel-iron-chromium alloy with additions of molybdenum, copper and titanium. Commonly referred to as Incoloy 825, this alloy is recognised for its excellent corrosion resistance in challenging environments, including those with sulfuric and phosphoric acids, and outstanding resistance to pitting and crevice corrosion, as well as to chloride-ion stress corrosion cracking.

## **KEY FEATURES**

- Excellent corrosion resistance
- High temperature resistance
- Optimal longevity in challenging environments
- General weldability

CHEMICAL PROPERTIES											
Nickel (Ni)	Chromium (Cr)	Iron (Fe)	Molybdenum (Mo)	Copper (Cu)	Manganese (Mn)	Titanium (Ti)	Silicone (Si)	Aluminium (Al)	Carbon (C)	Sulphur (S)	
38-46%	19.5-23.5%	22%	2.5-3.5%	1.5-3%	1%	0.6-1.2%	0.5%	0.2%	0.05%	0.03%	

MECHANICAL PROPERT	IES
Tensile strength (N/mm²)	590
Yield strength (N/mm²)	241
Elongation (% in 4D)	30
Hardness - Rockwell (HRB) max	80-85
Hardness - Brinell (HB) max	320

PHYSICAL PROPERTIES							
Density (kg/m³)	8140						
Modulus of elasticity (Gr	196						
M	0-100°C (µm/m/°C)	14.0					
Mean coefficient of	0-350°C (µm/m/°C)	14.9					
thermal expansion	0-538°C (µm/m/°C)	15.4					
Thermal	at 100°C (W/m.K)	11.1					
conductivity	at 500°C (W/m.K)	13.5					
Specific Heat 0-100°C (3	440						
Electrical resistivity (nΩ.	113						
Melting point (°C)	1400						

### **MARKET SECTORS**



Oil & Gas **Industry** 

Equipment for sour gas, tubing and piping



Chemical **Processing** 

Reactors, vessels, heat exchangers, piping systems, valves



Marine Equipment

Seawater piping systems, heat exchangers, valves, ship fittings



**Power** Generation

Heat exchangers, steam generators, components



Pulp & Paper Industry

Digesters, bleach plants, processing equipment



**Pollution** Control

Scrubbers, ductwork, waste incinerators, reactors